




MBA

Balls - Stainless Steel - 304 Grade



A2 Grade. Low magnetic permeability. Good corrosion resistance. Excellent for use in handling foodstuffs. Tolerances available on request. Grade 100.

Non annealed. Hardness: Rockwell C: 25-39. Specific Gravity: 7.916

Low magnetic permeability. Good corrosion resistance. Excellent for use in handling foodstuffs.

Note! Increase in magnetic permeability may occur due to the grinding process and can be relieved by heating to over 1000 Deg C.

This catalogue to be read in conjunction with information at <http://www.minibearings.com.au/fcal/balls/>

Balls - Stainless Steel - 304 Grade

Part Number	Diameter (D) mm	Material	Precision Grade	Hardness	Properties	Colour	Specific Gravity
BL-01.000-304-G100	1.000	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-01.588-304-G100	1.588	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-02.000-304-G100	2.000	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916

E&OE Pricing and all details subject to change without notice - Copyright Miniature Bearings Australia Pty Ltd
MBA Size Listings are a guide to sizes only and must not be solely relied on for critical design information.

Balls - Stainless Steel - 304 Grade

Part Number	Diameter (D) mm	Material	Precision Grade	Hardness	Properties	Colour	Specific Gravity
BL-02.381-304-G100	2.381	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-03.000-304-G100	3.000	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-03.175-304-G100	3.175	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-03.969-304-G100	3.969	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-04.000-304-G100	4.000	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-04.762-304-G100	4.763	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-05.556-304-G100	5.556	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-06.350-304-G100	6.350	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-07.144-304-G100	7.144	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-07.938-304-G100	7.938	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-08.731-304-G200	8.731	304 Grade Stainless	Grade 200	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916

**E&OE Pricing and all details subject to change without notice - Copyright Miniature Bearings Australia Pty Ltd
MBA Size Listings are a guide to sizes only and must not be solely relied on for critical design information.**

Balls - Stainless Steel - 304 Grade

Part Number	Diameter (D) mm	Material	Precision Grade	Hardness	Properties	Colour	Specific Gravity
BL-09.525-304-G100	9.525	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-11.113-304-G100	11.113	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-12.700-304-G100	12.700	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-14.288-304-G200	14.288	304 Grade Stainless	Grade 200	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-15.875-304-G100	15.875	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
# BL-17.463-304-G100	17.463	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-19.050-304-G100	19.050	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-22.225-304-G100	22.225	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916
BL-25.400-304-G100	25.400	304 Grade Stainless	Grade 100	Rockwell C: 25-39	Low magnetic permeability. Good corrosion resistance	Silver	7.916

E&OE Pricing and all details subject to change without notice - Copyright Miniature Bearings Australia Pty Ltd
MBA Size Listings are a guide to sizes only and must not be solely relied on for critical design information.

MBA **MINIAMNURD**
BEARINGS
 Australia Pty Ltd



ABN 94 069 113 800

DISTRIBUTED BY

Ask us to put your name and address here

<http://www.minibearings.com.au/product>
 Ph +61 7 3349 1224
 Fax +61 7 3349 3801

Catalogue requests to catalogues@minibearings.com.au

